KERRAFRONT

TECHNICAL DATA SHEET

| Profil e type | Kerrafront |
|---------------------------------------|---|
| Material | PVC-UE |
| Mass [mb] | FS-201 - 0,920 FS-202 - 1,500 FS-301 -1,750 FS-302 -1,600 FS-304 -1,600 |
| Total width / coverage | FS-201- 219/180 mm FS-202 - 371/332 mm FS-301- 359/320 mm FS-302 - 372/332 mm FS-304- 374/332 mm |
| Thickness | FS-201- 6,5 -18 mm FS-202 - 6,5 -18 mm FS-301- 8,4-18 mm FS-302 - 6,5 -18 mm FS-304 - 6,4 -18 mm |
| Packing | FS-201 - 2 pc. / 2,16 m ² FS-202 - 2 pc. / 3,984 m ² FS-301 - 2 pc. / 3,84 m ² FS-302 - 2 pc / 3,984 m ² FS-304 - 2 pc. / 3,984 m ² |
| Sto rag e | Profiles made offoamed PVC should be stored indoors, on a dry, flat and stable base, ensuring no direct contact with the ground. While remaining in their packaging, they should not be stored in places where they can be exposed to direct sunlight |
| Tools | Conventional carpentry tools for cutting or drilling should be used for processing foamed PVC profiles and finishing strips. Use fine-toothed saws; mechanical tools for processing should be used at the same or faster speeds as for processing wood. |
| Fastening | Installation takes place on a wooden or metal substructure with the use of metal screws according to the specification in the assembly manual. |
| Factory mounting holes | Yes. Oblong holes for mechanical fasteners, |
| Installation temperature | Installation should take place at an ambient temperature between $+5^{\circ}$ C and $+30^{\circ}$ C. Before installation, the profiles should be able to adapt to the weather conditions at the installation site for about 24 hours |
| Important installation information | See assembly instructions. |



| Maintenance | Facade profiles made of foamed PVC are ready-made products that do not require painting and maintenance. In order to maintain aesthetics, the facades should be cleaned at least once a year or depending on how dirty it is. Use mild detergents. Do not use water at a temperature above +40° C, strong detergents, bleaching agents, solvents, strong acids and bases, and abrasives. |
|-------------------|--|
| Usage Information | During use, possible color changes due to solar radiation, in moderate climate conditions, with air temperatures not exceeding $+40^{\circ}$ C, at an altitude of up to 1800 m above sea levei. may be homogeneous and not exceeding the 3rd degree on a gray scale (EN-20105- A02) |

| Essential characteristics | Performance properties | Assessment methods |
|--|---|------------------------------|
| Impact resistance | Not less than: 3J (-20,03) 6J (23,03) | PN-EN 13245-22009/AC2010 |
| Rei ease of hazardous substances | NPD | PN-EN 13245-22009/AC2010 |
| Reaction to fire | D-s3;d2 | PN-EN 13501-12019-02 |
| Durability | | |
| Wood design | A4.60 | |
| Colorblend | A4.60 | PN-EN 13245- |
| Painted | A4.60 | 22009/AC2010 |
| Monocolor | A6,4.60 | |
| Veneered | AS.60 | |
| Color change | Greyscale not more than 3 | PN-EN 20105-A021996 |
| Fastening strength | A6.65 | PN-EN 13245- 22009/AC2010 |







